

WATERPROOFING

CCW-702LV

Description

CCW-702LV is a quick-drying, solvent-based, high-tack adhesive specifically designed to promote maximum adhesion of CCW membranes.

Installation

Apply by medium nap roller (3/8" nap for best results) or brush in an even film at 300 to 350 square feet per gallon. Allow adhesive to dry for 20 minutes minimum at 75°F. Drying times may vary at lower temperatures. Porous substrates will result in reduced coverage rates for proper adhesion. Adhesives have a satisfactory cure when surface is tacky, but will not transfer when touched. Apply only on areas to be waterproofed the same day. Re-apply if membrane is not applied in the same day as the primer or if the area becomes wet or contaminated. When used in adverse climatic conditions (i.e. humid, cool, etc.) or on a porous substrate, or on a porous substrate, an additional curing time will be required.

Surface Preparation for Gypsum-Sheathing with Glass-Mat Facers:

When installing CCW sheet membranes and sheet flashings over gyp-sheathing with glass-mat facers, coverage rates for contact adhesives and primers will depend on the porosity and texture of the sheathing and will vary substantially by gypsum-sheathing brand and manufacturer. To achieve consistent contact adhesive and/or primer coverage with adequate tack, it may be necessary to decrease the coverage rate (i.e. increase the amount applied) of the contact adhesive and/or primer and/or the application of multiple coats. CCW Contact adhesives and primers shall be allowed to dry completely (lower temperatures will extend drying time) before additional coats are applied or membranes installed. Caution should be taken as contact adhesives and/or primers applied to gyp-sheathings with glass-mat facers will take longer to dry than other substrates. Multiple adhesion tests should be performed randomly to verify proper application of primer and ensure a successful application.

Warnings and Hazards

Flammable liquid and vapors. Use only with adequate ventilation and avoid breathing vapors. Refer to MSDS for other important warnings and product safety information.

Storage

Store at 35° to 110°F (2° to 43°C).

Packaging

5-gallon pails, 45 pails per pallet. P/N 316148

Typical Properties

Property	Results
Weight per Gallon	7.5 lbs 7.5 lbs
Solids Content	46% by wt
VOC Content	less than 250 g/l
Color	Plumb Red
Flash Point	-4°F (-20°C)
Adhesion to Concrete	11.0 lb/in
Viscosity	200 cps
Storage Temp	35°F to 110°F
Performance Index	*

Limited Warranty

Carlisle Coatings & Waterproofing Incorporated (Carlisle) warrants this product to be free of defects in workmanship and materials only at the time of shipment from our factory. If any Carlisle materials prove to contain manufacturing defects that substantially affect their performance, Carlisle will, at its option, replace the materials or refund its purchase price. This limited warranty is the only warranty extended by Carlisle with respect to its materials. There are no other warranties, including the implied warranties of merchantability and fitness for a particular purpose. Carlisle specifically disclaims liability for any incidental, consequential, or other damages, including but not limited to, loss of profits or damages to a structure or its contents, arising under any theory of law whatsoever. The dollar value of Carlisle's liability and buyer's remedy under this limited warranty shall not exceed the purchase price of the Carlisle material in question.